

CERAM  
Queens Road, Penkhull  
Stoke-on-Trent  
ST4 7LQ England

**Tel:** +44 (0) 1782 746476

**Fax:** +44 (0) 1782 412331

**E-mail:** enquiries@ceram.com

**www.ceram.com/building**

## TEST REPORT

Client's name and address

Mr S Pearson  
Tersus Ltd  
Challenge Court  
Bishop's Castle  
Shropshire  
SY9 5DW

Client's Mark      Terrazzo Tiles  
Your Reference     Order N°: PO2513  
Date Received      24.09.08  
Laboratory No.    (086436) – 29413  
Date Tested        29.09.08  
Date Issued        09.10.08

### REPORT OF TESTS ON THE UNPOLISHED SLIP RESISTANCE VALUE OF TERRAZZO TILES

#### 1. SAMPLES

5 of – Terrazzo Tiles

#### 2. TEST PROCEDURE

The pavers were tested for Unpolished Slip Resistance Value (USRV) in accordance with BSEN 13748-1: 2004 Terrazzo Tiles – Part 1: terrazzo tiles for internal use' Part 5.7 using a Pendulum Friction Tester incorporating a slider 76.20mm wide. The samples were tested in both directions longitudinally on the same wearing surface (directions A and B.)

#### 3. RESULTS

Results are given in the following table.

Sample N°	USRV					MEAN
	1	2	3	4	5	
Direction A	39	41	39	32	22	35
Direction B	41	40	37	27	20	33
Overall Mean USRV						34

*cm*

The mean USRV of the samples tested is: 34

**End of Test Report**

  
Authorised signatory  
C. Mullington